

OCEANZ PA12

Chemische bestendigheid // Chemical resistance

Medium		Concentration	6 months, 20°C	4 weeks, 60°C
Aceton	<i>Aceton</i>	100	++	++
Accu zuur	<i>Battery acid</i>	10	-	--
Mierenzuur	<i>Formic acid</i>		++	o
Ammonia	<i>Ammonia</i>	Concentraat	++	++
Aniline	<i>Aniline</i>	100	+	
Appelsap	<i>Apple juice</i>		++	++
Asfalt	<i>Asphalt</i>		++	++
Bariumzouten	<i>Barium salts</i>		++	++
Benzine	<i>Petrol</i>		++	++
Benzeen	<i>Benzene</i>	100	++	o
Bier	<i>Beer</i>		++	
Remvloeistof	<i>Break fluid</i>		++	++
Butaangas	<i>Butane gas</i>	100	++	++
Butaanvloeistof	<i>Butane liquid</i>	100	++	
Boter	<i>Butter</i>		++	
Chroomzuur	<i>Chromic acid</i>	10	--	--
Cyclohexanon	<i>Cyclohexanone</i>	100	++	o
Dibutylftalaat	<i>Dibutylphthalate</i>		++	++
Diethylether	<i>Diethyl-ether</i>	100	+	
Diocetylftalaat	<i>Diocetylphthalate</i>		++	++
Dixan®Base	<i>Dixan®Base</i>	Useable	++	++
Azijnzuur	<i>Acetic acid</i>	10	++	-
Ethylacetaat	<i>Ethyl-acetate</i>		++	+
Ethanol	<i>Ethyl-alcohol</i>	100	++	+
Vis	<i>Fish</i>		++	
Fluorwaterstofzuur	<i>Hydrofluoric acid</i>	40	-	--
Antivries	<i>Anti-freezer</i>		++	++
Afwasmiddel	<i>Dish cleaner</i>		++	++
Glycerine	<i>Glycerine</i>	100	++	++
Glycol	<i>Glycol</i>	100	++	++
Stookolie	<i>Fuel oil</i>		++	++
Koffie	<i>Coffee</i>	50	++	
Kaliumhydroxide	<i>Potassium hydroxide</i>		++	++
Kaliumchloraat	<i>Potassium chlorate</i>		+	o
Kaliumpermanganaat	<i>Potassium permanganate</i>		-	--
Lijnzaadolie	<i>Linseed oil</i>		++	++
Methanol	<i>Methanol</i>	100	++	+
Melk	<i>Milk</i>		++	++
Melkzuur	<i>Lactid acid</i>	10	+	o
Natriumchloride	<i>Sodium-chloride</i>		++	++

Natriumhypochloriet	<i>Sodium-hypochloride</i>	5	+	-
Natriumhydroxide	<i>Sodium hydroxid</i>	50	++	++
Ozon	<i>Ozone</i>		o	
Paraffine	<i>Paraffin</i>	100	++	++
Persil®Base	<i>Persil®Base</i>	useable	++	++
Petroleum	<i>Petroleum</i>	100	++	++
Propaangas	<i>Propane gases</i>	100	++	++
Pyridine	<i>Pyridine</i>	100	++	
Rum	<i>Rum</i>	40	++	++
Salpeterzuur	<i>Nitric acid</i>	10	--	--
Zoutzuur	<i>Salt acid</i>	10	--	--
Groene zeep	<i>Soft soap</i>		++	++
Zwavel	<i>Sulfur</i>	100	++	++
Zwavelzuur	<i>Sulfur acid</i>	10	+	-
Zeewater	<i>Sea water</i>		++	++
Siliconenolie	<i>Silicon oil</i>		++	++
Eetbare olie	<i>Edible oil</i>		++	++
Tolueen	<i>Toluene</i>	100	++	-
Tomatensap	<i>Tomato juice</i>		++	+
Trichloorethyleen	<i>Trichlorethylene</i>	100	o	-
Water	<i>Water</i>	100	++	+
Waterstofperoxide	<i>Hydrogen-peroxide</i>	30	++	
Whiskey	<i>Whiskey</i>	40	++	
Xyleen	<i>Xylene</i>	100	++	o
Citroenzuur	<i>Citric acid</i>		++	o
Citroensap	<i>Lemon juice</i>		++	++
Suikeroplossing	<i>Sugar solution</i>	every	++	++

zeer // very vrijwel // mostly matig // limited nauwelijks // not very

niet // not

All information in this data sheet is based on appropriate testing further details of which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. The data are subject to change without notice as part of our continuous development and improvement processes.

Visit Oceanz

Maxwellstraat 21, 6716 BX EDE

T: +31 (0) 318 769 077

M: info@oceanz.eu

W: www.oceanz.eu

The content of this material datasheet may be subject to copyright restrictions. Quoted results are compiled from Oceanz test data, suppliers source data, and may contain data values from other material specific sources.